







## IV. CONCLUSIONS AND RECOMMENDATIONS

In this paper, compaction pressure and compaction displacement behavior were investigated for loose briquetting using grass and leaves. In addition, the combustion behavior for solid round and round hollow briquettes were investigated. Based on the obtained results, the following conclusions can be made:

- The density of loose biomass composed of equal quantities of leaves and grass depends on pressure
- An optimum or saturation density occurs at a pressure of 35 MPa beyond which no further increase in density is observed
- The optimum density of loose biomass briquettes composed of equal quantities of dry leaves and grass is 1250 kg/m<sup>3</sup>
- Solid round briquette combustions achieved a maximum temperature of 210°C while the hollow round briquette achieved 280°C after five minutes of combustion
- The hollow round briquette was found to be the preferred geometry for combustion efficiency

The current work was conducted on two selected loose biomass stock without due consideration of energy content or other properties. The stock used was mainly based on availability. It is recommended that this work be conducted for a range of biomass stock especially that which is available in remote communities such as agricultural waste (maize leaves, rice stalks etc.) to ensure that developed technologies are effective for target communities.

Further work is also required to determine the optimum shape and geometry for effective combustion and energy extraction for such applications as space heating and cooking. Energy balance tests should yield more positive indication of the best geometries for such applications.

## REFERENCES

- [1] Eskom Holdings SOC Limited, "What is load shedding?," Eskom Holdings SOC Limited, 2015. [Online]. Available: <http://loadshedding.eskom.co.za/LoadShedding/Description>. [Accessed 25 June 2015].
- [2] K. Masekoameng, T. Simalenga and T. Saidi, "Household Energy Needs and Utilisation Patterns in the Giyani Rural Communities of Limpopo Province, South Africa," *Journal of Energy in Southern Africa*, vol. 16, no. 3, pp. 4-5, 2005.
- [3] T. Beringer, W. Lucht and S. Schaphoff, "Bioenergy Production Potential of Global Biomass Plantations Under Environmental and Agricultural Constraints," *Bioenergy*, vol. 3, pp. 299-312, 2011.
- [4] R. M. Shuma, D. M. Madyira, G. A. Oosthuizen and T. N. Makonese, "Energy Content and Combustion Behaviour of Loose Biomass Available in Limpopo," in *International Conference on the Domestic Use of Energy*, Cape Town, 2015.
- [5] Coal Marketing International, "Coal Basics," Coal Marketing International, 2012. [Online]. Available: <http://www.coalmarketinginfo.com/coal-basics/>. [Accessed 27 June 2015].
- [6] S. H. Sengar, A. G. Mohod, Y. P. Khandetod, S. S. Patil and A. D. Chendake, "Performance of Briquetting Machine for Briquette Fuel," *International Journal of Energy Engineering*, vol. 2, no. 1, pp. 28-34, 2012.
- [7] J. Tumuluru, L. G. Tabil, Y. Song, K. L. Iroba and V. Meda, "Effect of Process Variables on the Quality of Attributes of Briquettes from Wheat, Oat, Canola and Barley," in *Asabe Annual International Meeting*, 2011.
- [8] D. M. Madyira and N. Tayisepi, "Viability of Monitoring Biomass Solar Drying Using Humidity," in *Manufacturing Systems and Operations Management (MPSOM) Proceedings*, Victoria Falls, 2015.
- [9] M. T. L. Lekwana, D. M. Madyira, G. A. Oosthuizen and T. N. Makonese, "CFD Evaluation of Premix and Non-premix Models as Suitable Representatives of Fixed Bed Combustor Freeboard," in *International Conference on Domestic Use of Energy*, Cape Town, 2015.