



Fig. 5. Effect of CNC loading on (a) mechanical tensile strength and (b) tensile modulus

IV. CONCLUSIONS

Cellulose nanocrystals from rice husk had been isolated using acid hydrolysis method. The diameter of cellulose nanocrystals recorded by transmission electron microscope (TEM) is 12 ± 3.04 nm. Plasticized cassava starch/cellulose biocomposite films were successfully prepared via solution casting technique. Reinforcement effect of filler was investigated at the variation of CNC loadings (0-10wt.%). It was found that the addition of CNC enhance the mechanical properties of the nanocomposite films with the 6 wt% CNC showed the highest tensile strength. Incorporating cellulose

nanocrystals also leads to a decrease in water uptake, and increased film crystallinity.

ACKNOWLEDGMENT

The authors would like to express their gratitude towards Universiti Kebangsaan Malaysia for allowing this research to be carried out. Financial supports were from Ministry of Higher Education under research grant number FRGS/2/2013/SG06/UKM/02/2 and Zamalah Universiti Penyelidikan from Universiti Kebangsaan Malaysia.

REFERENCES

- [1] M. J. John and S. Thomas, *Carbohydrate Polymer* (2008).
- [2] N. L. Garcia, L. Ribba, A. Dufresne, M. Aranguren, and S. Goyanes, *Carbohydrate Polymers*, 84, 203–210 (2011).
- [3] A. J. Svagan, M. S. Hedenqvist, and L. Berglund, *Composites Science and Technology*, 69, 500-506 (2009).
- [4] E.M. Teixeira, D. Pasquini, A.A.S. Curvelo, E. Corradini, M.N Belgacem, and A. Dufresne, *Carbohydrate Polymers* 78, 422-431 (2009).
- [5] Y. Chen, C. Liu, P. R. Chang, X. Cao and D. P. Anderson, *Carbohydrate Polymer* 76, 607-615 (2009).
- [6] H. Kargarzadeh, I. Ahmad, I. Abdullah, A. Dufresne, S. Y. Zainudin and R. M. Sheltami, *Cellulose DOI* 10.1007/s10570-012-9684-6 (2012).
- [7] J.O. Zoppe, M.S. Peresin, Y. Habibi, R.A. Venditti and O.J. Rojas, *ACS Applied Materials and Interfaces*, 1, 1996-2004 (2009).
- [8] M. N. Anglès, & A. Dufresne, *Macromolecules*, 33, 8344–8353 (2000).